



**TECHNICAL DATA**

**Hybrid Polymer**

<b>Shrinkage</b>	nil	nil
<b>Flow</b>	5 Bar / 3mm / 23°C	140 g/min
<b>Skin cure</b>	23°C 50% R.H.	8 minutes
<b>Non-adhering</b>	23°C 50% R.	25minutes
<b>Full cure time</b>	23°C 50% R.H.	24hrs - 6mm 48hrs - 7/12mm

<b>E-Modulus 100%</b>	172 N/cm <sup>2</sup> / 1,72 Mpa
<b>Volume shrinkage after cure</b>	< 3%
<b>Hardness – DIN 53505</b>	60 Shore A
<b>Tensile strength :</b>	265 N/cm <sup>2</sup> / 2,65 Mpa
<b>Thermal stability:</b>	-40°C till + 120°C Peak: 155°C max. 30min.

**Elongation at rupture – DIN 53504** > 350 %

**Non toxic**  
**EC1 & EC1 A+ Certified**  
**Chemical resistance**

**Good:** Water, seawater, aliphatic solvents, oils ,greases  
Diluted organic acids.

**Dirt attachment:** Practically none

**Moderate:** Esters, Ketones, Aromatics, chlorine for swimming pools chlorinated solvents.

**Bad:** Concentrated Acids

**Shelf life:** 18 months

- 1) Measured to ISO 9040
- 2) Measured to DIN 53504
- 3) Measured to DIN 53505

All above tests according to ISO 11.600 25HM  
ETAG 022 Annex E,B & Additional tests of Annex F.  
ISEGA Food Approval.

**CT1 Danmark, Svalk Handel ApS.**  
**Mårslet Byvej 18, 8320 Mårslet**

**Tlf : +4586290900 Fax : +4586293944**

**Mail: [info@ct1danmark.com](mailto:info@ct1danmark.com) Web:[www.ct1danmark.com](http://www.ct1danmark.com)**

All information, including illustrations, is believed to be reliable. Users however, should independently evaluate the suitability of each product for their application. C-TEC makes no warranties of the accuracy of completeness of the information, and disclaims any liability regarding its use. C-TEC only obligations are those in the standard terms and conditions of sale of this product, and in no case will C-TEC be liable for any incidental, indirect or consequential damages arising from the sale, resale, use or misuse of this product. (20150312)



## APPLICATIONS

- For all applications, including bathrooms and general building maintenance CT1 replaces: Wood and P.U. adhesives, silicone sealants,, sanitary silicone sealants, acrylic sealants, butyl rubber sealants.
- As a universal adhesive CT1 bonds to most surfaces and does not attack synthetic material.
- On mirrors (Apply in vertical strips), on natural stone (does not bleed through), polyester, polystyrene foam, wet surfaces, even under water
- Repaintable with all common paints.
- For application advice on powder coated substrates contact powder coating manufacturer.
- **DIRECTION FOR USE:**
  - Before use ensure the cartridge has been stored at room temperature
  - Cut the Cartridge at the nose
  - Cut off nozzle at desired dimensions
  - Use a Mastic Gun
  - Apply on a clean, degreased surface
  - Finish off the joints with MULTISOLVE
- **CT1: DELIVERY FORM**
  - In Recyclable 290ml Cartridges or New 200ml No-Gun Required - Automatic Dispenser.
  - **Colours Available in 290ml Cartridge:** Clear, white, black, grey, light grey, oak & silver.

CT1 Danmark, Svalk Handel ApS.  
Mårslet Byvej 18, 8320 Mårslet  
Tlf : +4586290900 Fax : +4586293944

Mail: [info@ct1danmark.com](mailto:info@ct1danmark.com) Web: [www.ct1danmark.com](http://www.ct1danmark.com)

All information, including illustrations, is believed to be reliable. Users however, should independently evaluate the suitability of each product for their application. C-TEC makes no warranties of the accuracy of completeness of the information, and disclaims any liability regarding its use. C-TEC only obligations are those in the standard terms and conditions of sale of this product, and in no case will C-TEC be liable for any incidental, indirect or consequential damages arising from the sale, resale, use or misuse of this product. (20150312)